

Information about the content

Scope:	Plansee SE	Prepared/Updated:	Resch Joachim
		Released:	Glatz Wolfgang
Valid from:	18-Jun-2021	Controlled:	PSE-020

This document is subject to electronic version control – confirm revision status before using.

This specification covers tantalum ribbons in melting quality.

1 Dimensions and tolerances

1.1 Thickness- and Width tolerances

Thickness [mm]	Tolerance ± mm	Width [mm]	Tolerance < 100 mm [± mm]	Tolerance ≥ 100 mm [± mm]	
≥ 0,050 – ≤ 0,080	0,008	6 – 152,4	0,050	0,100	annealed
> 0,080 – ≤ 0,100	0,008	6 – 152,4	0,050	0,100	
> 0,100 – ≤ 0,120	0,010	6 – 152,4	0,050	0,100	
> 0,120 – ≤ 0,150	0,010	10 – 152,4	0,100	0,200	
> 0,150 – ≤ 0,300	0,010	10 – 120	0,100	0,200	
> 0,300 – 0,400	0,015	10 – 120	0,100	0,200	

Other dimensions upon request.



Details to our certificates
at www.plansee.com



2 Physical and mechanical product properties

Density ^{a)} $\geq 16,6 \text{ g/cm}^3$

Hardness Vickers: ^{b)} Thickness $\geq 0,15 \text{ mm}$: $\leq 100 \text{ HV}$

Tensile Test: ^{c)}	Thickness mm	Tensile strength	0,2%-Yield Strength	Elongation
		min. MPa	min. MPa	min. %
	$\geq 0,050 - \leq 0,080$	250	165	8
	$> 0,080 - \leq 0,100$	250	165	15
	$> 0,100 - 0,400$	250	165	25

- a) The density cannot be determined with sufficient accuracy for small material thickness below 1 mm. Due to the high degree of deformation during production, it is assumed that the theoretical density (above given value) is achieved.
- b) The actual value quoted in certificates corresponds to the mean-value of a representative control sample. Due to the low required test load, hardness is not specified for sheets $< 0,15 \text{ mm}$.
- c) Samples are taken parallel to the rolling direction.

Remarks: All TaM-ribbons are delivered recrystallized ($\geq 90 \%$ recrystallized in micrograph).

2.1 Surface condition

Appearance: The material will be of uniform quality, free from foreign matter, splits and fractures.

Surface defects and geometric variations are assessed in the frame of visual inspection.

Surface Roughness:	Cold rolled, bright	(Thickness $\geq 0,050 - 0,400 \text{ mm}$):	$R_a \leq 0,50 \mu\text{m}$
	Cold rolled, dull	(Thickness $\geq 0,050 - 0,400 \text{ mm}$):	$R_a \leq 1,00 \mu\text{m}$



Details to our certificates
at www.plansee.com



3 Chemical composition

Main and minor components	Plansee		Standard	EU- Directive
	Content		ASTM B708 (R05200)	RoHS ^{a)}
Ta	99,95 % ^{b)}		balance	-
Impurities	Max. values [µg/g]		Max. values [µg/g]	Max. values [µg/g]
	Typical	Guaranteed		
Fe	5	100	100	-
Mo	10	100	200	-
Nb	19	400	1000	-
Ni	5	50	100	-
Si	10	50	50	-
Ti	1	50	100	-
W	20	100	500	-
C	10	30	200	-
H	4	15	15	-
N	5	50	100	-
O ^{c)}	13	100	250	-
Cd	1	10	-	100
Hg ^{d)}	-	1	-	1000
Pb	-	10	-	1000
Cr (VI)	-	-	-	1000
Organic impurities (e.g. PBB, PBDE, PFOS, PFOA)	- **)	- **)	-	1000

a) EU-directives 2015/863/EU, 2011/65/EU and 2000/53/EC

b) Metallic Purity without Nb

c) Due to technical measurement reasons the upper specification limit for O can only be determined for the prematerial with a thickness of ≥ 1 mm.

d) Initial value

***) The presence of Cr (VI) and organic impurities can definitely be excluded because of the production process (multiple heat treatments at temperatures above 1000 °C in HV-atmosphere).

The chemical composition is checked by means of random sampling. The sampling inspection plan, analysis and evaluation methods are determined in the internal instruction PSE-020-WI-003. The application of the measured values for the chemical analysis is defined in PSE-680-WI-001.

Remarks: The specified physical and chemical characteristics are disclosed not regarding measurement accuracy.



Details to our certificates
at www.plansee.com



4 Packaging, labelling, storage and certification

4.1 Packaging, labelling and storage

Standard individual packing: The ribbons are wound on appropriate spools, depending on their dimensions and are sealed in a plastic bag together with a dehydrating agent. The packaging ensures avoidance of mechanical damage, moisture, oxidation and other sources of contamination during transport and handling.

Each package will be provided with a label with the following information:

Producer's name:	Plansee
Plansee order number:	
Lot number:	
Material number:	
Material:	TaM
Dimension:	thickness, width
Quantity:	Total quantity in kg
Date:	

The material must be kept in a dry place and protected from mechanical damage. It is best to keep the material in the original packing until used.

Special packing: (extra costs will be invoiced)

Special packing should be used if the sheets are stored under unusual conditions or aggressive atmosphere (e.g. sea air, ...).

4.2 Inspection documents

Following inspection documents will be supplied upon customer request according to EN 10 204:

Test report 2.2

Plansee confirms with this test report that the delivered product meets the specification and gives details of the material properties according to ongoing production surveillance, not directly related to the particular production batch.

Inspection certificate 3.1 (extra costs will be invoiced)

An inspection officer from Plansee confirms with this inspection certificate that the delivered product meets the specification and gives test results related to the particular production batch.



Details to our certificates
at www.plansee.com



PRODUCT SPECIFICATION

5 Order instructions

Please quote following information when ordering:

- Product description
- Quality (the number of this specification must be mentioned)
- Thickness, width
- Quantity in kg
- Required certificate and content in case of a 3.1 inspection certificate
- *For special packing:* Specification of packaging

For further information on our delivery possibilities. please look into our <http://www.plansee.com>

6 Referenced standards

The standards applied for the test methods are listed in the Plansee standard infobase and are made available upon request.

Changes to last version:

Replacement for PSE-605-PS-020 Rev.03

- Section 1.1 Dimensions and thickness tolerances $\geq 0,050$ mm / unannealed cancelled
- Section 2: Physical and mechanical properties for thickness $\geq 0,050$ mm
- Section 2.1 Surface roughness for thickness $\geq 0,050$ mm



Details to our certificates
at www.plansee.com

