

**Information about the content**

<b>Responsible area:</b>	Plansee SE	<b>Prepared/Updated:</b>	See SAP-DMS
		<b>Released:</b>	See SAP-DMS
<b>Valid from:</b>	02-Jun-2020	<b>Controlled:</b>	PSE-020

This document is subject to electronic version control – confirm revision status before using.

*This specification covers MoOxTa14 sputtering targets.*

## 1 Dimensions and tolerances

The MoOxTa14 sputtering targets are produced according to Plansee SE drawings with the dimensions, tolerances and surface finish specified in these construction drawings.

### 1.1 Bonding position

The target position on the backing plate is defined as follows:

- Long direction = actual measurement  $\pm 0,5$  mm from the backing plate end where the water cooling ports are located. Actual measurement is defined as distance from new backing plate end where the water cooling ports are located to the edge of the target.
- Short direction = actual measurement  $\pm 0,5$  mm from both backing plate ends. Actual measurement is defined as distance from the lateral end of the backing plate to the lateral edge of the target.

### 1.2 Warp

The warp after bonding will be less than 1,0 mm on plus side and less than 1,0 mm on minus side for targets **smaller than 800 mm** backing plate length.

The warp after bonding will be less than 1,0 mm on plus side and less than 2,0 mm on minus side for **800 to 1600 mm** backing plate length target.

The warp after bonding will be less than 1,5 mm on plus side and less than 3,0 mm on minus side for **1600 to 3000 mm** backing plate length target.

### 1.3 Target height

Target height from backing plate surface will be defined by H in the following equation  
(Target thickness) < H < (Target thickness + 1,5 mm)

## 2 Physical and mechanical product properties

**Guaranteed Density:** MoOxTa14:  $\geq 4,8$  g/cm<sup>3</sup>

### 2.1 Surface condition

**Appearance:** According to the drawing the specified areas of the target and / or the backing plate are blasted.

The Targets will have no cracks, abrasions and discoloration. Inhomogeneity and discolouration of the surface can occur and are related to the different phase alignment and the resulting interference.

### 3 Chemical composition

Main and minor components	Plansee MoOxTa14	EU-Directive
	content [%]	RoHS <sup>a)</sup>
<b>Mo</b>	<b>59,1 ± 2,0 wt.%</b>	-
<b>O</b>	<b>balance</b>	-
<b>Ta</b>	<b>13,8 ± 1,0 wt.%</b>	-
<b>Purity</b>	<b>Min. 99,9 %</b>	-
<b>Impurities</b>	<b>Max. values [µg/g] <sup>b)</sup></b>	<b>Max. values [µg/g] <sup>b)</sup></b>
	<b>Guaranteed</b>	
C	<b>100</b>	-
Fe	<b>30</b>	-
Cd	<b>5</b>	100
Hg <sup>c)</sup>	<b>1</b>	1000
Pb	<b>5</b>	1000

a) EU-directives 2015/863/EU, 2011/65/EU and 2000/53/EC

b) µg/g ≙ ppm (mass fraction)

c) Initial value / first up

**Remarks:** The specified physical and chemical characteristics are disclosed not regarding measurement accuracy.

## 4 Packaging, labelling, storage and certification

### 4.1 Packaging, labelling and storage

*Standard individual packing:* The target is vacuum-sealed in a vinyl pack, which is put into a transportation box.

*Each package will be provided with a label with the following information:*

<b>producer's name:</b>	Plansee SE
<b>product description incl. dimension:</b>	
<b>part number:</b>	
<b>order number:</b>	
<b>machining batch no. and serial no.:</b>	
<b>weight:</b>	kg

**The targets must be kept in a dry place and protected from mechanical damage.** The shelf time for the vacuum-packed targets shall be 6 months from the shipping date under the following storage conditions <sup>a)</sup>. However, the customer is recommended to use the targets within 3 months.

a) **Storage conditions:** temperature:  $22 \pm 4$  °C; relative humidity of the air:  $\leq 50$  %; atmospheric pressure: approx. 1000 mbar.

### 4.2 Certification

All targets manufactured by Plansee SE will be certified including the following information:

#### 4.2.1 Identification

The order number, target batch number and target number are indicated.

#### 4.2.2 Chemical composition

Inspection certificate 2.2 according to EN 10204:2004 (chemical elements see section 3).

#### 4.2.3 Dimensions

Actual values of length, width and thickness of the sputtering target.

#### 4.2.4 Weight

Actual measured value.

## 5 Order instructions

Please quote following information when ordering:

- dimensions
- quality (the number of this specification **must** be mentioned)
- quantity (number of targets)
- bonded version (yes/no)
- *for special packing:* specification of packaging

For further information on our delivery possibilities, please consider our <http://www.plansee.com>

## 6 Referenced standards

The standards applied for the test methods are listed in the Plansee standard InfoBase and are made available upon request.

## MoOxTa14 Sputtering Targets

PS – PRODUCTSPECIFICATION

4 / 4

### Changes to last version

Replacement for	Changes to last version
-	▪ new specification

## Appendix 1

### General product information for MoOxTa14 Targets

The following physical data are for reference only and no guarantee values.

physical property		unit	value
bending strength	at 20°C	MPa	50
linear thermal expansion	at 20°C-200°C	1/K	3,5 x 10 <sup>-6</sup>
thermal conductivity	at 20°C	W/mK	4,0
optical appearance			dark